


Technical Information of T.U.X KRC-HR

21-Nov-23

Grade	KRC-HR		Method
Thickness	60		
Haze [% / 4 sheets]	53		JIS K7105
COF [Tan θ] Outside/Outside	0.45		Incline Board
Wet tension [mN/m]	41		JIS K6768
Tensile Strength [MPa]	MD	50	JIS K7127
	TD	39	
Tensile Elongation [%]	MD	771	JIS K7127
	TD	1173	
Young's Modulus [Mpa]	MD	452	JIS K7127
	TD	560	



Data described in this catalog are representative figures obtained by measurement under specific conditions but not specifications values
ข้อมูลนี้อธิบายไว้เพื่อเอกสารฉบับนี้ เป็นผลการทดสอบเบื้องต้นจากการทดสอบกลุ่มตัวอย่างภายใต้เงื่อนไขเฉพาะเท่านั้น ไม่ใช่ข้อมูลสเปคของผลิตภัณฑ์