


Technical Information of T.U.X VCS-ST

08-Mar-22

Grade	VCS-ST		Method
	40	50	
Thickness	40	50	
Haze [% / 4 sheets]	23	23	JIS K7105
COF [Tan θ] Outside/Outside	0.09	0.10	Incline Board
Wet tension [mN/m]	37	37	JIS K6768
Tensile Strength [MPa]	MD	53	JIS K7127
	TD	40	
Tensile Elongation [%]	MD	720	JIS K7127
	TD	880	
Young's Modulus [Mpa]	MD	100	JIS K7127
	TD	110	
Impact Strength [J] Room Temp.	1.50	1.73	ASTM D3420



Data described in this catalog are representative figures obtained by measurement under specific conditions but not specifications values
ข้อมูลนี้อธิบายไว้ในเอกสารฉบับนี้ เป็นผลการทดสอบเบื้องต้นจากการทดสอบกลุ่มตัวอย่างภายใต้เงื่อนไขเฉพาะเท่านั้น ไม่ใช่ข้อมูลสเปคของผลิตภัณฑ์